SUPERSHIELD DURACLEAN A+ BONG MO



Ultra-premium interior paint

DESCRIPTION

SUPERSHIELD DURACLEAN A+ BONG MO - Ultra premium interior paint is made from pure Acrylic (with Biomass balance), provides easy cleaning that leaves no stain after cleaning. It made indoor air quality the best by Air Detoxify Technology which gives odor-less and Formaldehyde abatement indoor air. Moreover, it gives long life prevention of bacteria over color coating without harmful side effect to human being. Excellent fungal prevention with advanced technology of nearly zero V.O.C (Volatile Organic Compound).

TYPICAL USES

SUPERSHIELD DURACLEAN A+ BONG MO - Ultra premium interior paint is suitable for new and previously painted interior masonry surface such as concrete, mortar, cement plaster, brick, gypsum board, light cement board, etc. It is highly recommended for children room, hospital, kinder garden, restaurant and hallway, etc.

PHYSICAL PROPERTIES

Components: Pure Acrylic, pigments, additives & waterColor: Refer to catalogue and TCW fan-deck

Finish: Sheen
 Solids by volume (%): 40 ± 2

• **Theoretical coverage:** 10.0 – 13.3 m²/liter/coat

Actual surface coverage will be depended on the spreading of paint film ability, dry film thickness, surface irregularities, technique and wastage during painting.

· Volatile Organic

Compound (VOCs): $\leq 30 \text{ g/L}$

• The drying time, Relative Humidity (RH) 50%

 Substrate temperature 	20°C	30°C	35°C
○ Surface (touch) dry	1h	0.5h	0.3h
○ Hard dry	6h	4h	3h
 Painting interval, minimum 	4h	2h	1.5h

The actual drying time and painting interval time may be longer or shorter, depending on the ambient temperature, film thickness, ventilation, humidity, number of paint coatings, etc.

RECOMMENDED PAINT SYSTEM

PAINT SYSTEM	PRODUCT	NUMBER OF COAT(s)
Putty	TOA PRO PUTTY	2
Primer	SUPERSHIELD SUPER SEALER	1
Topcoat	SUPERSHIELD DURACLEAN A+ BONG MO	2

Issued date: 30/07/2021 Page: 1/3

This Technical Data Sheet supersedes those previously issued.

^{*} Biomass balance: help to save fossil resources and protect the environment.

APPLICATION INSTRUCTION

SURFACE PREPARATION

New surface

Let the concrete, cement plaster and mortar must be cured at least 28 days in ambient condition (average temperature is 25°C -30°C, relative humidity <75%), the surface moisture is not exceed 16% (specialized measuring testing equipment). pH value is about 6-9.

Remove all dust, grease, wax, laitance, chalking and others contamination from the surface by specialized machine as: grinding, sanding, vacuum cleaner, high pressure water jet and proper cleanness.

Apply 2 coats TOA PRO PUTTY for smooth surface.

Old surface

Remove all dust, fungus, algae, loose old paint or others contamination from the surface by specialized machine as: grinding, sanding, vacuum cleaner, high pressure water jet and proper cleanness.

Then, treat the areas attacked by fungus, algae with proper chemicals.

Wash the surface if required, let it fully dry, the substrate moisture must be lower than 16% (specialized measuring testing equipment)

Repair the damaged area. Cracks bigger than 0.1mm must be fixed and make smooth by TOA PRO PUTTY.

Apply 1 coat of premium multipurpose primer - TOA HYDRO QUICK PRIMER for chalky or powdery surface after making surface clean.

APPLICATION

Application tools: Brush, roller, conventional spray

Guiding data for airless spray

- **Nozzle tip size** : 0.021 – 0.027" - **Spray angle degrees** : 65 – 80°

- **Pressure at nozzle** : 140 – 190 Kg/cm² (2.000-2.600 Psi)

Film thickness:

		Min	Standard	Max
-	Dry film thickness:	30µm	35µm	40μm
_	Wet film thickness:	75um	87.5um	100um

Film thickness will vary and is calculated as average.

Dilution: The paint is ready to use after proper stirring until homogeneous.

If thinning is required, clean water may be added up to a maximum of 5%.

CERTIFICATES

Green Label No. 032-246-3579 - Singapore Environment Council

Conformity Regulation certified: QCVN 16:2019/BXD - National Technical Regulations on Products, Goods of Building Materials for Emulsion paint (Interior & Exterior)

Issued date: 30/07/2021 Page: 2/3

Conformity Standard certified: TCVN 8652:2012 – National standards on wall emulsion paints – specifications.

Conformity Regulation certified: QCVN 08:2020/BCT - National technical regulation on the limits of lead content in paints

Test report of microbial resistance by test method: JIS L1902:2015/Pasteur Institute, Ho Chi Minh City.









STORAGE & HANDLING

Store in a dry, cool, good ventilation area, shaded area. Keep out of reach of children. Storage temperature about 25°C - 35°C.

Ensure that the right primer is used. Should use putty and let it thoroughly cure before painting.

Stir well before use and once opened, entire contents should be used.

Apply when temperature is from 10°C to 35°C and relative humidity <75%. Surface temperature must be 3°C higher than the dew point.

HEALTH AND SAFETY

Please do not handle until all safety precautions have been read and understood.

Keep away from heat, sparks, open flame, hot surface. No smoking.

Wear protective gloves, respirator, eye protection, protective clothing.

Avoid contact with skin, eyes or ingestion. Go right to the nearest health center for help in case of ingesting paint or paint contacts with eyes.

Avoid release to the environment. Treat discarded paint according to environmental law.

See more guidelines in the Safety Data Sheet.

PACKING SIZE

15 liter; 5 liter; 1 liter;

DISCLAIMER

The information in this data sheet is given to the best of TOA's knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond TOA's control. TOA cannot guarantee anything only the quality of the product itself. TOA reserve the right to change given data without further notice.

TOA PAINT VIETNAM CO., LTD.

Factory: Lot L2,3; Road No.2, Tan Dong Hiep A IP,

Di An city, Binh Duong province

Tel: 0274 3775 678 – 3775004 Fax: 0274 3775005

Website: www.toagroup.com.vn

OFFICE

Flat 8, Room 8.5, E-Town 3 Building, 364 Cong Hoa street, ward 13, Tan Binh Ho Chi Minh city

Tel: 028 38131999 Fax: 028 38131113

Issued date: 30/07/2021 Page: 3/3