

# EPOGUARD PRIMER – TWO PACK EPOXY PRIMER



[www.toagroup.com.vn](http://www.toagroup.com.vn)

## DESCRIPTION

**EPOGUARD PRIMER** is a high-build Epoxy / Polyamide primer with Zinc Phosphate contained.

## TYPICAL USE

Used as a high-build rust-preventing epoxy primer for steel structure, tank, pipe, bridge and chemical plant.

## PRODUCT DATA

**Components** : Binders, pigments, additives and solvents

**Color** : Red iron oxide / Gray

**Paint film appearance** : Semi-Gloss

**Solid by volume** : 53 ± 2 %

**Theoretical coverage** : 3.5 – 10.6 m<sup>2</sup>/liter/coat

*Actual surface coverage will be depended on spreading ability of paint film, dry film thickness, surface irregularities, technique and wastage during painting.*

### Volatile organic compounds

**(VOCs)** : ≤ 450 g/L

**Flash point** : appx.21°C

### Drying time (at relative humidity (RH) 50% & dry film thickness (DFT) 100µm):

	25°C	30°C	35°C
○ Surface temperature	25°C	30°C	35°C
○ Surface dry (touch dry)	1h	45 minutes	30 minutes
○ Hard dry	8h	6h	4h
○ Painting interval, minimum	12h	10h	8h
○ Pot life	10h	8h	6h

*Actual drying time and painting interval time may be longer or shorter than provided data, depended on environmental temperature, dry film thickness, ventilation, humidity and number of coating applied, etc.*

## RECOMMENDED PAINT FILM SYSTEM:

SYSTEM	PRODUCT	COAT(S)	DRY FILM THICKNESS
<i>For metal surfaces:</i>			
Primer	Epoguard Primer	1	100µm
Topcoat	Epoguard Enamel (For inside area) or Topguard (For outside area)	2	50µm

## APPLICATION INSTRUCTION

- SURFACE PREPARATION

# Technical data sheet

## ➤ Steel:

- Remove all oil, grease, dirt, oxide and other foreign material by cleaning per SSPC-SP1, Solvent Cleaning.

### + High Quality:

- Should be blast cleaned in accordance with NACE No.2 / SSPC-SP10 / ISO 8501:1 / SIS Sa 2.5 to a near-white finish using a suitable abrasive.

### + Medium Quality:

- Treatment by using Power tool cleaning in accordance with SIS St 3 or SSPC-SP3.

**Remark:** The surface must be thoroughly dry and the protective coating applied within 4 hours to cleaned surface.

## ➤ Before Recoat by Topcoat:

- Remove all oil, grease, dirt, oxide and other foreign material by cleaning per SSPC-SP1, Solvent Cleaning before coating.
- If primer / first topcoat layer was applied over last 7 days, gives surface cleaning by sand paper no. 320-400 then follow SSPC-SP1, Solvent Cleaning before next coat applied.

## ▪ MIXING RATIO

Mixing ratio	Part A	Part B
By volume	6	1
By weight	9	1

*Stir well Part A and Part B separately.*

*To ensure painting system achieves drying time and designed physical properties, recommended mixing ratio should be strictly followed.*

*Gradually pour Part B into Part A, stir well in 2 – 3 minutes with dedicated stirrer until homogeneous. Leave the mixture for stabilization in 5 minutes before applying.*

## ▪ APPLICATION

### Equipment / methods:

Brush, roller, conventional spray, airless spray

For airless spray gun:

- Nozzle tip size : 0.012" – 0.019"
- Angle to the surface : 65° – 80°
- Pressure at nozzle : 140 – 190 Kg/cm<sup>2</sup> (2.000 – 2.600 Psi)

### Paint film thickness:

	Min	Standard	Max
- Dry film thickness (DFT):	50µm	100µm	150µm
- Wet film thickness (WFT):	94µm	188µm	283µm

*Film thickness will vary and is calculated as average.*

### Dilution ratio:

Paint is ready to use after proper stirring until homogeneous.

Add in **maximum 5% TOA epoxy thinner #31 by volume** if thinning is necessary.

*Dilution percentage is depending on ambient temperature, relative humidity, paint film thickness, equipment and application method.*

# Technical data sheet

## CERTIFICATION

TCVN 9014:2011 – National technical regulation on Epoxy resin paints certified.

QCVN 08:2020/BCT – National technical regulation on the limits of lead content in paints certified.



## HANDLING AND STORAGE

The product must be stored in accordance with national regulations.

Store in a dry, cool, good ventilation area; far from heat, open flame, flammable materials.

Tightly closed when not in use.

Keep out of reach of children.

Stir well before use, paint should be used up when lid opened.

Storage temperature is recommended at 25°C – 30°C.

Do not apply when temperature is lower than 15°C or higher than 40°C.

Do not apply when relative humidity exceeds 75%.

Surface temperature should be at least 3°C higher than the dew point of the air.

## HEALTH AND SAFETY

Please do not handle until all safety precautions have been read and understood.

Keep away from heat, sparks, open flame, hot surface. No smoking.

Wear protective gloves, respirator, eye protection, protective clothing.

Avoid contact with skin, eyes or ingestion. Go right to the nearest health center for help in case of ingesting paint or paint contacts with eyes.

Avoid release to the environment. Treat discarded paint according to environmental law.

See more guidelines in the Safety Data Sheet.

## PACKAGING

	net volume (liter)	volume of can (liter)
<b>EPOGUARD PRIMER Part A</b>	4.2   16.8	5   20
<b>EPOGUARD PRIMER Part B</b>	0.7   2.8	1   5

## SHELF LIFE

24 months from manufacturing day when stored at 25°C – 30°C

# Technical data sheet

---

## DISCLAIMER

The information in this data sheet is given to the best of TOA's knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, TOA cannot guarantee anything only the quality of the product itself. TOA reserves the right to change given data without notice.

*Revision: 01*

*Issue: 02.12.2022*

### **TOA PAINT VIETNAM CO., LTD**

Factory: Lot L2,3; Road No.2, Tan Dong Hiep A IP,  
Di An city, Binh Duong province  
Tel: 0274 3775 678 – 3775004      Fax: 0274 3775005  
Website : [www.toagroup.com.vn](http://www.toagroup.com.vn)

### **OFFICE**

Flat 8, Room 8.5, E-Town 3 Building,  
364 Cong Hoa street, ward 13,  
Tan Binh district, Ho Chi Minh city  
Tel: 028 38131999      Fax: 028 38131114

---

Issued: 02/12/2022

Page: 4/4

This Technical Data Sheet supersedes those previously issued.

The Technical Data Sheet (TDS) is recommended to be read in conjunction with the Safety Data Sheet (SDS) for this product.