

MANDARIN DUCK - ALKYD HIGH GLOSS ENAMEL PAINT



www.toagroup.com.vn

DESCRIPTION

MANDARIN DUCK Alkyd High Gloss Enamel Paint is high quality Alkyd paint without using Lead and Mercury in manufacturing process. This is the safe paint for health with features: glossy surface, high coverage, anti-fungus, beautiful colors.

TYPICAL USE

MANDARIN DUCK Alkyd High Gloss Enamel Paint is suitable for woods, metals and other surfaces which primed properly. This product could be used for both interior and exterior.

PRODUCT DATA

- **Components** : Binders, pigments, additives and solvents
- **Color** : Refer to catalogue
- **Paint film appearance:** Gloss (except #222; #888 matt)
- **Solid by volume** : 48 ± 3 %
- **Theoretical coverage** : 12.0 – 16.0 m²/liter/coat
Actual surface coverage will be depended on spreading ability of paint film, dry film thickness, surface irregularities, technique and wastage during painting.
- **Volatile organic compounds (VOCs)** : ≤ 450 g/L (except #000 ≤ 500 g/L)
- **Flash point** : appx.42°C
- **Drying time (at relative humidity (RH) 50% & dry film thickness (DFT) 30µm - 40µm):**

○ Surface temperature	25°C	30°C	35°C
○ Surface dry (touch dry)	4h	3h	2h
○ Hard dry	16h	10h	8h
○ Painting interval, minimum	16h	12h	10h

Actual drying time and painting interval time may be longer or shorter than provided data, depended on environmental temperature, dry film thickness, ventilation, humidity and number of coating applied, etc.

RECOMMENDED PAINT FILM SYSTEM:

SYSTEM	PRODUCT	COAT(S)	DRY FILM THICKNESS
<i>For metal surfaces:</i>			
Primer	MANDARIN DUCK QD Red or Grey Oxide Primer	1 – 2	45µm
Topcoat	MANDARIN DUCK alkyd high gloss enamel paint	2	35µm
<i>For wood surface:</i>			
Primer	Appropriate primer for wood surface	1 – 2	-
Topcoat	MANDARIN DUCK alkyd high gloss enamel paint	2	35µm

Technical data sheet

APPLICATION INSTRUCTION

▪ SURFACE PREPARATION

- Make sure the surface is dry and clean, free from grease, oil, waxy contamination, rust or mill scale.

For industrial purpose:

- Oil and grease must be cleaned in accordance with SSPC-SP1, Solvent Cleaning.
- Surface should be blast cleaned, at least achieved Sa 2.0 – Sa 2.5 (ISO 8501-1:2007).
- With area cannot be blast cleaned, use power tools to clean the surface at least achieved St2 – St3 (ISO 8501-1:2007).

▪ APPLICATION

Equipment / methods:

Brush, roller, conventional spray, airless spray

For airless spray gun:

- Nozzle tip size : 0.013" – 0.021"
- Angle to the surface : 65° – 80°
- Pressure at nozzle : 140 – 190 Kg/cm² (2.000 – 2.600 Psi)

Paint film thickness:

	Min	Standard	Max
- Dry film thickness (DFT):	30µm	35µm	40µm
- Wet film thickness (WFT):	63µm	73µm	83µm

Film thickness will vary and is calculated as average.

Dilution ratio:

Paint is ready to use after proper stirring until homogeneous.

Add in maximum 5% TOA alkyd thinner #21 by volume if thinning is necessary.

Dilution percentage is depending on ambient temperature, relative humidity, paint film thickness, equipment and application method.

Dilute paint with solvent other than TOA alkyd thinner #21 might lead paint film turn yellowing excessively, especially for #MD111 & #HE100.

CERTIFICATION

TCVN 5730:2008 – National technical regulation on Alkyd paints certified.

QCVN 08:2020/BCT – National technical regulation on the limits of lead content in paints certified.



Technical data sheet

HANDLING AND STORAGE

The product must be stored in accordance with national regulations.

Store in a dry, cool, good ventilation area; far from heat, open flame, flammable materials.

Tightly closed when not in use.

Keep out of reach of children.

Stir well before use, paint should be used up when lid opened.

Storage temperature is recommended at 25°C – 30°C.

Do not apply when temperature is lower than 15°C or higher than 40°C.

Do not apply when relative humidity exceeds 75%.

Surface temperature should be at least 3°C higher than the dew point of the air.

HEALTH AND SAFETY

Please do not handle until all safety precautions have been read and understood.

Keep away from heat, sparks, open flame, hot surface. No smoking.

Wear protective gloves, respirator, eye protection, protective clothing.

Avoid contact with skin, eyes or ingestion. Go right to the nearest health center for help in case of ingesting paint or paint contacts with eyes.

Avoid release to the environment. Treat discarded paint according to environmental law.

See more guidelines in the Safety Data Sheet.

PACKAGING

17.5 liter; 3 liter; 0.8 liter and 0.375 liter

SHELF LIFE

48 months from manufacturing day when stored at 25°C – 30°C

DISCLAIMER

The information in this data sheet is given to the best of TOA's knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, TOA cannot guarantee anything only the quality of the product itself. TOA reserves the right to change given data without notice.

Revision: 01

Issue: 02.12.2022

Technical data sheet

TOA PAINT VIETNAM CO., LTD

Factory: Lot L2,3; Road No.2, Tan Dong Hiep A IP,
Di An city, Binh Duong province
Tel: 0274 3775 678 – 3775004 Fax: 0274 3775005
Website : www.toagroup.com.vn

OFFICE

Flat 8, Room 8.5, E-Town 3 Building,
364 Cong Hoa street, ward 13,
Tan Binh district, Ho Chi Minh city
Tel: 028 38131999 Fax: 028 38131114