



TOA NANOCLEAN BONG MO / SIEU BONG

Premium interior paint

DESCRIPTION

TOA NANOCLEAN BONG MO / SIEU BONG – premium interior paint is made from pure Acrylic with Hybrid Nano technology, keeps your house safe, clean and durable.

+ Silver Nano particles (nano silver) in TOA NANOCLEAN Bong mo / Sieu bong can kill up to 99.9% bacteria (*) help to protect your whole family's health and fresh living environment.

+ Hybrid Nano – Germany nano technology with 1/billion particle size, improve waterproofing and stain resistance, gives smooth surface, easy washing all types of hard stains such as: oil, grease, tomato, chalk marks, etc.

+ TOA NANOCLEAN Bong mo / Sieu bong has been certificated as "GREEN", environmentally friendly product. No added lead, mercury, APEO, Formaldehyde in the formula.

+ More ever, TOA NANOCLEAN Bong mo / Sieu bong have got other outstanding properties: smooth surface, anti-fungus and algae, easy to touch up, high hiding, good coverage, odorless and long lasting color.

* Tested with 2 common bacteria Escherichia Coli and Staphylococcus Aureus.

TYPICAL USES

TOA NANOCLEAN BONG MO / SIEU BONG is suitable for new and previously painted interior masonry surface such as concrete, mortar, cement plaster, brick, gypsum board, light cement board, etc. It highly recommended for area that required extra hygiene such as hotel, restaurant, hospital, infirmary, healthcare center, etc.

PHYSICAL PROPERTIES

• **Components:** Pure Acrylic, pigments, additives & water

• **Color:** Refer to catalogue and TCW fan-deck

• **Finish:** Sheen / High Sheen

• **Solids by volume (%):** 42 ± 2

• **Theoretical coverage:** 10.5 – 14.0 m²/liter/coat

Actual surface coverage will be depended on the spreading of paint film ability, dry film thickness, surface irregularities, technique and wastage during painting.

• **Volatile Organic**

Compound (VOCs): ≤ 30 g/L for Sheen, ≤ 70 g/L for High Sheen (Gloss)

• **The drying time, Relative Humidity (RH) 50%**

○ Substrate temperature	20°C	30°C	35°C
○ Surface (touch) dry	1h	0.5h	0.3h
○ Hard dry	6h	4h	3h
○ Painting interval, minimum	4h	2h	1.5h

Technical Data Sheet

The actual drying time and painting interval time may be longer or shorter, depending on the ambient temperature, film thickness, ventilation, humidity, number of paint coatings, etc.

RECOMMENDED PAINT SYSTEM

PAINT SYSTEM	PRODUCT	NUMBER OF COAT(S)
Putty	TOA WALL MASTIC INTERIOR	2
Primer	TOA NANOCLEAN PRIMER	1
Topcoat	TOA NANOCLEAN Bong mo / Sieu bong	2

APPLICATION INSTRUCTION

▪ SURFACE PREPARATION

New surface

Let the concrete, cement plaster and mortar must be cured at least 28 days in ambient condition (average temperature is 25°C -30°C, relative humidity <75%), the surface moisture is not exceed 16% (specialized measuring testing equipment). pH value is about 6-9.

Remove all dust, grease, wax, laitance, chalking and others contamination from the surface by specialized machine as: grinding, sanding, vacuum cleaner, high pressure water jet and proper cleanness.

Apply 2 coats TOA WALL MASTIC INTERIOR for smooth surface.

Old surface

Remove all dust, fungus, algae, loose old paint or others contamination from the surface by specialized machine as: grinding, sanding, vacuum cleaner, high pressure water jet and proper cleanness.

Then, treat the areas attacked by fungus, algae with proper chemicals.

Wash the surface if required, let it fully dry, the substrate moisture must be lower than 16% (specialized measuring testing equipment)

Repair the damaged area. Cracks bigger than 0.1mm must be fixed and make smooth by TOA WALL MASTIC INTERIOR

Apply 1 coat of premium multipurpose primer - TOA HYDRO QUICK PRIMER for chalky or powdery surface after making surface clean.

▪ APPLICATION

Application tools: Brush, roller, conventional spray

Guiding data for airless spray

- **Nozzle tip size** : 0.021 – 0.027"
- **Spray angle degrees** : 65 – 80°
- **Pressure at nozzle** : 140 – 190 Kg/cm² (2.000-2.600 Psi)

Film thickness:

	Min	Standard	Max
- Dry film thickness:	30µm	35µm	40µm
- Wet film thickness:	71µm	83µm	95µm

Film thickness will vary and is calculated as average.

Technical Data Sheet

Dilution: The paint is ready to use after proper stirring until homogeneous.
If thinning is required, clean water may be added up to a maximum of 5%.

CERTIFICATES

Green Label No. 032-246-3500, 032-246-3502 - Singapore Environment Council
Conformity Regulation certified: QCVN 16:2019/BXD - National Technical
Regulations on Products, Goods of Building Materials for Emulsion paint (Interior
& Exterior)

Conformity Standard certified: TCVN 8652:2012 - National standards on wall
emulsion paints - specifications

Test report of microbial resistance by test method: JIS L1902:2015/Pasteur
Institute, Ho Chi Minh City

Conformity Regulation certified: QCVN 08:2020/BCT - National technical
regulation on the limits of lead content in paints



STORAGE & HANDLING

Store in a dry, cool, good ventilation area, shaded area. Keep out of reach of children. Storage temperature about 25°C - 35°C.

Ensure that the right primer is used. Should use putty and let it thoroughly cure before painting.

Stir well before use and once opened, entire contents should be used.

Apply when temperature is from 10°C to 35°C and relative humidity <75%.
Surface temperature must be 3°C higher than the dew point.

HEALTH AND SAFETY

Please do not handle until all safety precautions have been read and understood.

Keep away from heat, sparks, open flame, hot surface. No smoking.

Wear protective gloves, respirator, eye protection, protective clothing.

Avoid contact with skin, eyes or ingestion. Go right to the nearest health center for help in case of ingesting paint or paint contacts with eyes.

Avoid release to the environment. Treat discarded paint according to environmental law.

See more guidelines in the Safety Data Sheet.

PACKING SIZE

15 liter; 5 liter; 1 liter

DISCLAIMER

The information in this data sheet is given to the best of TOA's knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond TOA's control. TOA cannot guarantee anything only the quality of the product itself. TOA reserve the right to change given data without further notice.

Technical Data Sheet

TOA PAINT VIETNAM CO., LTD.

Factory: Lot L2,3; Road No.2, Tan Dong Hiep A IP,

Di An city, Binh Duong province

Tel: 0274 3775 678 – 3775004

Fax: 0274 3775005

Website : www.toagroup.com.vn

OFFICE

Flat 8, Room 8.5, E-Town 3 Building,

364 Cong Hoa street, ward 13, Tan Binh

Ho Chi Minh city

Tel: 028 38131999

Fax: 028 38131113